



PATENT ABSTRACTS OF JAPAN

(11) Publication number: **10036487 A**(43) Date of publication of application: **10.02.98**

(51) Int. Cl.

C08G 61/00
C07D333/08
C07D333/18
C07F 7/08
C09K 11/06
H05B 33/14
// C07C 13/567
C07C255/33
C07C381/12
C07D207/335
C07D209/86
C07D307/36

(21) Application number: **09069479**(22) Date of filing: **24.03.97**(30) Priority: **16.05.96 KR 96 9616449**(71) Applicant: **KOREA ADVANCED INST OF SCI
TECHNOL**

(72) Inventor: **KIN TEIYUPU**
CHO KENNAN
KIN TOEI
KIN EICHURU
RI JUNEI
KIN ZAIKEI


(54) FLUORENE POLYMER FOR EL ELEMENT AND
EL ELEMENT USING THE SAME

COPYRIGHT: (C)1998,JPO



(57) Abstract:

PROBLEM TO BE SOLVED: To obtain a fluorescent material of a polymer-based EL element, which is produced by a simple process, has a well-defined structure of a final substance and is highly soluble in organic solvents by using a specified alternating fluorene copolymer.

SOLUTION: This material is an alternating fluorene copolymer represented by formula I (wherein R and R' are each H, a 22C or lower alkyl, a cycloalkyl, an alkoxy, an alkoxyalkyl, an alkoxyalkoxyalkyl, an alkoxyalkoxyalkoxyalkyl, a 6-18C aryl, an alkylthio or an aralkyl; X is H or cyano; Ar is a group of formula II or a group of formula III; R'' and R''' are each the same as R or R'; n' is 1-22; and n is 1-2,000). This copolymer or a mixture thereof with a general-purpose polymeric material is used as a luminescent material of an EL element.



I



II

III